

Universal Bases and Abutments



Important – Disclaimer of Liability

This product is part of an overall concept and may only be used in conjunction with the associated original products according to the instructions and recommendation of Nobel Biocare. Non-recommended use of products made by third parties in conjunction with Nobel Biocare products will void any warranty or other obligation, express or implied, of Nobel Biocare. The user of Nobel Biocare products has the duty to determine whether or not any product is suitable for the particular patient and circumstances. Nobel Biocare disclaims any liability, express or implied, and shall have no responsibility for any direct, indirect, punitive or other damages, arising out of or in connection with any errors in professional judgment or practice in the use of Nobel Biocare products. The user is also obliged to study the latest developments in regard to this Nobel Biocare product and its applications regularly. In cases of doubt, the user has to contact Nobel Biocare. Since the utilization of this product is under the control of the user, they are his/her responsibility. Nobel Biocare does not assume any liability whatsoever for damage arising thereof.

Please note that some products detailed in this Instruction for Use may not be regulatory cleared, released or licensed for sale in all markets.

Description

Universal bases and abutments are premanufactured dental implant abutments which can be directly connected to an endosseous dental implant to support the placement of a single unit screw-retained dental prosthesis.

An assortment of universal bases and abutments are available for use with the following implant systems:

- Universal Bases Conical Connection (CC) are available in NP/RP/WP platforms, feature a conical connection and can be used with Nobel Biocare’s NobelActive®, NobelParallel™ CC and/or NobelReplace® CC implant systems.
- Universal Abutments Nobel Biocare N1™ TCC are available in NP/RP platforms, feature a tri-oval conical connection and can be used with Nobel Biocare’s Nobel Biocare N1™ implant system.
- Universal Bases Tri-channel are available in NP/RP/WP platform, feature an internal tri-channel connection and can be used with Nobel Biocare’s NobelReplace®, Replace Select™ and/or NobelSpeedy® Replace™ implant systems.
- Universal Bases External Hex are available in NP/RP/WP platforms, feature an external hex connection and can be used with Nobel Biocare’s Brånemark System® and/or NobelSpeedy® Groovy implant systems.

Table 1 presents a summary of the available universal bases and abutments based on their connection type and identifies the available platforms and margin heights, as well as the compatible screwdriver and the specified tightening torque.

Universal Base/ Abutment for	Available platforms	Available margin heights	Tightening torque	Screwdriver
Conical connection (CC)	NP	1.5 mm	35 Ncm	Unigrip™
	RP	3.0 mm		
	WP			
Tri-oval conical connection (TCC)	NP	1.5 mm	20 Ncm	Omnigrip™ mini
	RP	3.0 mm		
Tri-channel	NP	1.5 mm	35 Ncm	Unigrip™
	RP	3.0 mm		
	WP			
External Hex	NP	1.5 mm	35 Ncm	Unigrip™
	RP	3.0 mm		
	WP			

Table 1 – Universal Bases and Abutments – Available Platforms and Margin Heights, Tightening Torques and Compatible Screwdrivers

Universal bases and abutments are co-packed with a clinical screw. Refer to Nobel Biocare Instructions for Use (IFU) IFU1057 for information regarding clinical screws. This IFU is available for download at ifu.nobelbiocare.com.

Universal bases featuring internal conical connection (all platforms), internal tri-channel connection (all platforms) and external hex connection (NP and RP platforms) are also co-packed with a burn-out coping. Universal bases featuring external hex connection (WP platform) do not come co-packed with a burn-out coping. Burn-out copings are intended for laboratory use only and are not intended for intraoral use.

Intended Use / Intended Purpose

Universal Bases and Abutments

Intended to be connected to an endosseous dental implant to support the placement of a dental prosthesis.

Indications

Universal bases and abutments are indicated to support the placement of single unit, screw- retained prosthetic restorations in the maxilla or mandible.

Contraindications

It is contraindicated to use universal bases and abutments in:

- Patients who are medically unfit for an oral surgical procedure.
- Patients in whom adequate sizes, numbers or desirable positions of implants are not reachable to achieve safe support of functional or eventually parafunctional loads.
- Patients who are allergic or hypersensitive to titanium alloy Ti-6Al-4V (90% titanium, 6% aluminum, 4% vanadium) and DLC (Diamond Like Carbon) coating.

In addition, it is contraindicated to place universal bases and abutments which feature a conical connection (CC), internal tri-channel connection or external hex connection in:

- Patients who are allergic or hypersensitive to Polyoxymethylene (POM).

Cautions

General

Close cooperation between surgeon, restorative dentist and dental laboratory technician is essential for successful implant treatment.

Nobel Biocare surgical instruments and prosthetic components must only be used with Nobel Biocare implants, as combining components that are not dimensioned for correct mating can lead to mechanical and/or instrumental failure, damage to tissue or unsatisfactory esthetic results.

When using a new device/treatment for the first time, working with a colleague who is experienced with the new device/treatment may help avoid possible complications. Nobel Biocare has a global network of mentors available for this purpose.

Before Surgery

In general, implant placement and prosthetic design must accommodate individual patient conditions. In case of bruxism, other parafunctional habits or unfavorable jaw relationships, reappraisal of the treatment option may be considered.

The device has not been evaluated in pediatric/adolescent patients and is not recommended for use in children. Routine treatment is not recommended for pediatric patients until the end of the jaw bone growth phase has been properly documented.

Pre-operative hard tissue or soft tissue deficits may yield a compromised esthetic result or unfavorable implant angulations.

All components, instruments and tooling used during the clinical or laboratory procedure must be maintained in good condition and care must be taken that instrumentation does not damage implants or other components.

At Surgery

Because of the small size of the devices, care must be taken that they are not swallowed or aspirated by the patient. It is appropriate to use specific supporting tools to prevent aspiration of loose parts (e.g. gauze, dental dam, or throat shield).

After Surgery

To help ensure a successful long-term treatment outcome, it is advised to provide comprehensive regular patient follow up after implant treatment and to inform the patient about appropriate oral hygiene.

Intended Users and Patient Groups

Universal bases and abutments are intended to be used by dental health care professionals.

Universal bases and abutments are intended to be used in patients subject to dental implant treatment.

Clinical Benefits and Undesirable Side Effects

Clinical Benefits Associated with Universal bases and abutments

Universal bases and abutments are a component of treatment with a dental implant system and/or dental crowns and bridges. As a clinical benefit of treatment, patients can expect to have their missing teeth replaced and/or crowns restored.

Undesirable Side Effects Associated with Universal bases and abutments

The placement of this device is part of an invasive treatment which may be associated with typical side effects such as inflammation, infection, bleeding, hematoma, pain, and swelling. During abutment placement or removal the pharyngeal reflex (gag reflex) may be triggered in patients with a sensitive gag reflex.

Implant abutments are part of a multi-component system that replaces teeth and as a result, the implant recipient may experience side effects similar to those associated with teeth, such as retained cement, calculus, mucositis, ulcers, soft tissue hyperplasia, soft and/or hard tissue recessions. Some patients may experience discoloration in the mucosal area such as graying.

Notice regarding serious incidents

For a patient / user / third party in the European Union and in countries with an identical regulatory regime (Regulation 2017/745/EU on Medical Devices); if, during the use of this device or as a result of its use, a serious incident has occurred, please report it to the manufacturer and to your national authority. The contact information for the manufacturer of this device to report a serious incident is as follows:

Nobel Biocare AB

www.nobelbiocare.com/complaint-form

Handling Procedure

A. Designing and Manufacturing the Restoration using a Conventional Press Workflow (Laboratory Procedure, not applicable for Universal bases external hex WP as those do not have a burn-out coping)

1. Preparation of the Universal Base or Abutment:
 - Hand-tighten the universal base or abutment onto the master cast using a compatible laboratory screw.
2. Preparation of the Burn-out Coping:
 - Seat the burn-out coping onto the universal base or abutment.
 - Adjust the height of the burn-out coping according to the required occlusal plane. Ensure the universal base or abutment remains fully covered.
3. Production:
 - Create a wax-up restoration and use the standard procedure to either press or cast a coping or full-contour crown.
4. Finalization and Bonding:
 - Once the restoration is produced, finalize it following the restorative material manufacturer's instructions.
 - Connect the universal base or abutment to a replica or protection analog using a laboratory screw.
 - Sandblast the contact surface of the universal base or abutment with aluminum oxide 50 µm at a maximum of 2 bar.
 - Clean the bonding surface of the universal base or abutment using a steam jet or an ultrasonic bath.

Caution Do not sandblast the seating area. During the blasting procedure, use a protection analog or implant replica to prevent any modification of the abutment/implant interface. The use of wax in the screw channel is not recommended.

- Bond the restoration to the universal base or abutment according to the cement manufacturer's instructions. Use only self-adhesive dental cement/bonding material suitable for zirconium dioxide ceramics or PMMA (Polymethylmethacrylate).

Caution The screw channel of the universal base or abutment needs to be blocked prior to bonding and cleaned thereafter from residues of the bonding material. Follow the bonding material manufacturer's guidelines.

- Disconnect the restoration from the replica/protection analog and send it to the clinician along with the clinical screw.

B. Designing and Manufacturing the Restoration using a CAD/CAM Workflow for Desktop Scanners (Laboratory Procedure)

1. Scanning the Master Cast:
 - Connect a position locator to the replica embedded in the master cast.
 - Scan the master cast following the instructions of the scanner manufacturer.
2. Designing the Restoration:
 - Import the scan file into the CAD software and choose the desired universal base or abutment based on the soft tissue anatomy.
 - Design the restoration using standard CAD tools. Make sure to respect the restorative material manufacturer's design specifications.
3. Production:
 - Send the design file to a milling unit or local production facility.
4. Finalization and Bonding:
 - Once the restoration is milled, finalize it following the restorative material manufacturer's instructions.
 - Sandblast the bonding surface of the restoration following the restorative material manufacturer's instructions.
 - Clean the restoration as recommended by the bonding material manufacturer.
 - Protect the screw channel and emergence profile of the abutment before sandblasting by connecting it to a replica or protection analog using the laboratory screw.

Caution The use of wax in the screw channel is not recommended.

- Sandblast the contact surface of the abutment with aluminum oxide 50 µm at a maximum of 2 bar.
- Clean the bonding surface using steam jet or an ultrasonic bath.

Caution Do not sandblast the seating area. During the blasting procedure, use a protection analog or implant replica to prevent any modification of the abutment/implant interface. The use of wax in the screw channel is not recommended.

- Bond the restoration to the universal base or abutment according to the cement manufacturer's instructions. Use only self-adhesive dental cement/bonding material suitable for zirconium dioxide ceramics or PMMA (Polymethylmethacrylate).

Caution The screw channel of the universal base or abutment needs to be blocked prior to bonding and cleaned thereafter from residues of the bonding material. Follow the bonding material manufacturer's guidelines.

- Disconnect the restoration from the replica/protection analog and send it to the clinician along with the clinical screw.

C. Designing and Manufacturing the Restoration using a CAD/CAM Workflow for Intra-oral Scanners (Clinical and Laboratory Procedure)

1. Intra-oral Scanning:
 - Connect a position locator to the implant in the patient's mouth.
 - Take an intra-oral scan of the patient following the instructions of the scanner manufacturer.

2. Designing the Restoration:

- Import the scan data into the CAD software and choose the desired universal base or abutment based on the soft tissue anatomy.
- Design the restoration using standard CAD tools.

3. Production:

- Send the design file to a milling unit or local production facility.

4. Finalization and Bonding:

- Once the restoration is milled, finalize it following the restorative material manufacturer's instructions.
- Sandblast the bonding surface of the restoration following the restorative material manufacturer's instructions.
- Clean the restoration as recommended by the bonding material manufacturer.
- Protect the screw channel and emergence profile of the abutment before sandblasting by connecting it to a replica or protection analog using the laboratory screw.

Caution The use of wax in the screw channel is not recommended.

- Sandblast the contact surface of the abutment with aluminum oxide 50 µm at a maximum of 2 bar.
- Clean the bonding surface using steam jet or an ultrasonic bath.

Caution Do not sandblast the seating area. During the blasting procedure, use a protection analog or implant replica to prevent any modification of the abutment/implant interface. The use of wax in the screw channel is not recommended.

- Bond the restoration to the universal base or abutment according to the cement manufacturer's instructions. Use only self-adhesive dental cement/bonding material suitable for zirconium dioxide ceramics or PMMA (Polymethylmethacrylate).

Caution The screw channel of the universal base or abutment needs to be blocked prior to bonding and cleaned thereafter from residues of the bonding material. Follow the bonding material manufacturer's guidelines.

- Disconnect the restoration from the replica/protection analog and send it to the clinician along with the clinical screw.

D. Placement of the Final Restoration (Clinical Procedure)

Ensure sufficient implant stability before beginning the prosthetic procedure.

Caution The final restoration and clinical screw must be cleaned, disinfected and sterilized prior to placement in the patient's mouth, following the instructions of the material manufacturer.

- Remove the healing cap or temporary restoration from the patient.
- Connect and hand-tighten the Universal Base/Abutment restoration using the clinical screw. It is recommended to verify the final abutment seating using radiographic imaging.
- Tighten the restoration according to Table 1 using dedicated screwdriver and Manual Torque Wrench prosthetic.

Caution Never exceed recommended maximum tightening torque for the screw. Overtightening of abutment may lead to a screw fracture.

Caution To tighten the abutment, the implant should be able to withstand the recommended tightening torque of the clinical screw.

- Block out the screw head before closing the screw access hole with composite.
- If removal of the restoration is needed, open the screw access and untighten the screw using the appropriate screwdriver.
- If the abutment cannot be removed, use the Abutment Retrieval Tool. Refer to Nobel Biocare Instructions for Use (IFU) IFU1096 for information regarding Abutment Retrieval Tool.

Materials

- Universal bases and abutments: Titanium alloy 90% Ti, 6% Al, 4% V according to ASTM F136 and ISO 5832-3.
- Burn-out Coping: Polyoxymethylene (POM).
- Clinical screws: Titanium alloy 90% Ti, 6% Al, 4% V according to ASTM F136 and ISO 5832-3 and DLC (Diamond Like Carbon) coating.

Sterility and Reusability Information

Universal bases and abutments are delivered non-sterile and are intended for single use.

The final restoration (comprised of the universal base or abutment with bonded restoration and clinical screw) must be cleaned and sterilized prior to intraoral use following the procedures in the Cleaning and Sterilization Instructions. During processing in the dental laboratory, the supra-construction can be cleaned as necessary without disinfection or sterilization.

Warning Use of non-sterile device may lead to infection of tissues or infectious diseases.

Caution Universal bases and abutments are single use products and must not be reprocessed. Reprocessing could cause loss of mechanical, chemical and/or biological characteristics. Reuse could cause local or systemic infection.

The Burn-out Coping is used in the dental laboratory only (no intraoral use) and has no cleaning and/or sterilization requirements.

Cleaning and Sterilization Instructions

Cleaning and sterilization instructions for supra-constructions that include non-metallic materials, which require cleaning and disinfection and/or sterilization prior to patient contact.

Clean, disinfect and/or sterilize the final restoration according to instructions of the restorative material manufacturer.

Magnetic Resonance (MR) Safety Information

MR Safety Information for Single Tooth Restoration

MRI Safety Information



Non-clinical testing has demonstrated the NobelProcera® FCZ Implant Crown is MR conditional. A patient with this device can be safely scanned in an MR system meeting the following conditions mentioned here below. Failure to follow these conditions may result in injury to the patient.

Nominal value(s) of Static Magnetic Field [T]	1.5-Tesla (1.5 T)	3-Tesla (3 T)
Maximum Spatial Field Gradient [T/m and gauss/cm]	Maximum spatial field gradient of 58.9 T/m (5,890 G/cm).	
RF Excitation	Circularly Polarized (CP).	
RF Transmit Coil Type	Whole body transmit coil.	
Maximum Whole-Body SAR [W/kg]	Inferior to the neck: 2.0 W/kg	Inferior to the xyphoid: 2.0 W/kg Between the xyphoid and neck: 1.0 W/kg Superior to the neck: 0.5 W/kg
Limits on Scan Duration	Under the scan conditions defined above, the dental implant systems are expected to produce a maximum temperature rise less than 6.0°C after 15 minutes of continuous scanning.	
MR Image Artifact	In non-clinical testing, the image artifact caused by the dental implant systems extend radially approximately 1.9 cm from the devices or device assemblies when imaged in a 3 T MRI system.	

Performance Requirements and Limitations

To achieve the desired performance, Universal bases and abutments must only be used with the products described in this Instructions for Use and/or in the Instructions for Use for other compatible Nobel Biocare products, and in accordance with the Intended Use for each product. To confirm the compatibility of products which are intended to be used in conjunction with Universal bases and abutments, check the color coding, dimensions, lengths, connection type and/or any direct marking as applicable on the products or product labeling.

Facilities and Training

It is strongly recommended that new and experienced users of Nobel Biocare products always go through special training before using a new product for the first time. Nobel Biocare offers a wide range of courses for various levels of knowledge and experience. For more information please visit www.nobelbiocare.com.

Storage, Handling and Transportation

The device must be stored and transported in dry conditions in the original packaging at room temperature and not exposed to direct sunlight. Incorrect storage and transportation may influence device characteristics leading to failure.

Disposal

Safely discard potentially contaminated or no longer usable medical devices as healthcare (clinical) waste in accordance with local healthcare guidelines, country and government legislation or policy.

Separation, re-cycling or disposal of packaging material shall follow local country and government legislation on packaging and packaging waste, where applicable.


Manufacturer and Distributor Information

Manufacturer



Nobel Biocare AB
PO Box 5190, 402 26
Västra Hamngatan 1
411 17 Göteborg
Sweden
www.nobelbiocare.com

UK Responsible Person



Nobel Biocare UK Ltd
4 Longwalk Road
Stockley Park
Uxbridge
UB11 1FE
United Kingdom

Distributed in Australia by

Nobel Biocare Australia Pty Ltd
Level 4, 7 Eden Park Drive
Macquarie Park, NSW 2113
Australia
Phone: +61 1800 804 597

Distributed in New Zealand by

Nobel Biocare New Zealand Ltd
33 Spartan Road
Takanini, Auckland, 2105
New Zealand
Phone: +64 0800 441 637

CE Mark for Class IIb Devices



UKCA Mark for Class IIb Devices



Note Regarding Canadian Device Licensure not all products described in the IFU may have a device licence according to Canadian law.

Basic UDI-DI Information

The following table lists the Basic UDI-DI information for the devices described in this IFU.

Product	Basic UDI-DI Number
Universal Bases CC NP/RP/WP	7332747000001697K
Universal Abutments Nobel Biocare N1™ TCC NP/RP	
Universal Bases Tri-Channel NP/RP/WP	
Universal Bases External Hex NP/RP/WP	

EN All rights reserved.


Nobel Biocare, the Nobel Biocare logotype and all other trademarks used in this document are, if nothing else is stated or is evident from the context in a certain case, trademarks of Nobel Biocare. Product images in this folder are not necessarily to scale. All product images are for illustration purposes only and may not be an exact representation of the product.

Symbols Glossary

The following symbols may be present on the device labeling or in information accompanying the device. Refer to the device labeling or accompanying information for the applicable symbols.



Authorized Representative in the European Community/ European Union



UK Responsible Person



Authorised Representative in Switzerland



Sterilized using Ethylene Oxide



Sterilized using irradiation



Sterilized using steam or dry heat



Batch code



Catalogue number



Unique Device Identifier



Serial number



Medical device



Magnetic resonance safe



Caution



Magnetic resonance conditional



Non-sterile



Contains hazardous substances



Contains or presence of DEHP phthalate



Contains or presence of natural rubber latex



Contains or presence of phthalate



Contains biological material of animal origin



CE mark



CE mark with Notified Body number



UKCA mark



UKCA mark with Approved Body number



Consult instructions for use



For prescription use only



symbol.glossary.nobelbiocare.com
ifu.nobelbiocare.com

Link to Online Symbols Glossary and IFU Portal



Date of manufacture



Manufacturer



Use-by date



Upper limit of temperature



Temperature limit



Do not resterilize



Do not re-use



Non-pyrogenic



Date



Tooth number



Patient number



Patient identification



Health care centre or doctor



Patient information website



EU Importer



Swiss Importer



Double sterile barrier system



Single sterile barrier system



Single sterile barrier system with protective packaging inside



Single sterile barrier system with protective packaging outside



Do not use if package is damaged and consult instructions for use



Keep away from sunlight



Keep dry